

3F, Building Block 2, No. 3400 Gonghexin Road,
Jing'an District - Shanghai 200436, P.R. CHINA
上海市静安区共和新路3400号2幢3层
Tél. : +86 21 68 55 50 32
Fax : +86 21 68 55 50 33
E-mail : ctcshanghai@ctcgroupe.com

Report No.: S201010849_1

21 October 2020

june.guo@pipchinaltd.com

APPLICANT: PROTECTIVE INDUSTRIAL PRODUCTS HONG KONG LTD., (C06226)

FLAT 1-11,
6/F KAR WAH INDUSTRIAL BUILDING
8 LEUNG YIP STREET
. YUEN LONG, N. T
HONG KONG

Date of receipt : 20 Oct. 2020
Testing period : 21 Oct. 2020
: 21 Oct. 2020

Buyer: ---

Style / Article no. : 16-VRX380
Test(s) requested : ---
Service : SHUTTLE
Brand / Section : ---
Season : ---
End use : ---
Factory name : ---
Factory code : ---

For CE Marking : Yes


Previous report : ---
Product category : ---
Product type : ---
Test stage : FIRST TEST
Supplier name : ---
Exported to : ---

1. Conclusion:

	Tests description	Conformity
	ANSI-ISEA 105: 2016	
1	Cutting resistance TDM	Level A3

Pass: requirements met Fail: requirements not met None: no requirement for this test N/A: not applicable

Approved by



Henry YAN
Laboratory Manager



Report No.: S201010849_1

21 October 2020

APPLICANT: PROTECTIVE INDUSTRIAL PRODUCTS HONG KONG LTD., (C06226)

2. Sample(s) description assigned by laboratory:

<u>Size</u>	<u>Analyzed product</u>	<u>Description</u>	<u>Sample information</u>
	GLOVE	black PU(HPPE(high performance polyethylene)/nylon/spandex) palm	



201010849

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.



Report No.: S201010849_1

21 October 2020

APPLICANT: PROTECTIVE INDUSTRIAL PRODUCTS HONG KONG LTD., (C06226)

3. GLOVE/

black PU (HPPE (high performance polyethylene)/nylon/spandex) palm

	Method	Client Requirement	Unit	Result	Conformity
(+) 5.1.1. Cutting resistance TDM Correction factor of the sharp edge of the blade with the neoprene Load for a distance of 20 mm cut Performance level	ASTM F2992 /F2992M - 15		g	0.98 1381 Level A3	

END OF TEST REPORT
Classification Table for Cut Resistance
(ANSI-ISEA 105)

Level	Weight (grams) needed to cut through material with 20 mm of blade travel
A1	>=200
A2	>=500
A3	>=1000
A4	>=1500
A5	>=2200
A6	>=3000
A7	>=4000
A8	>=5000
A9	>=6000

The report is issued by CTC Shanghai under its General Conditions printed overleaf. The results shown in this report refer only to the sample(s) tested. Except by special arrangement, the test items will not be retained by CTC Shanghai for more than 3 months. The test report shall not be reproduced, except in full, without the written approval of the testing laboratory.

To declare the conformity to the requirement, the uncertainty of measurement, associated to the test results, has not been taken into account.

